



Saturated Polyester Resins :

Code	Solvent	Mainly Technique Index						Features & Application
		Solid Content(100%)	Color	Appearance	Viscosity/ 25°C	OH value(100%)	Acid Value	
335	Ethers/Aromatics	58~62	≤1	Transparency	250~350/T-4	70~80	1~5	Fast drying, good leveling and weather resistant. Coil top coat
345	Ethers/Aromatics	58~62	≤3	Transparency	25~35/CPS	45~55	≤6	Coil coat, Coil Aluminum paint
301B	Ethers/Aromatics	58~62	≤3	Transparency	20~30/CPS	65	≤8	Excellent compatibility with epoxy resin, economic, coil top and back coat
315A	Ethers/Aromatics	58~62	≤1	Transparency	60~100/CPS	120	≤10	Fast drying, good hardness. Coil top coat and back coat
302B	Ethers/Aromatics	58~62	≤3	Transparency	35~45/CPS	50	≤6	Economic, coil top coat
382	Ethers/Aromatics	58~62	≤1	Transparency	20~30/CPS	85	≤6	Super weather resistant, coil coat
385	Ethers/Aromatics	58~62	≤1	Transparency	20~30/CPS	40~50	≤5	Good hardness, flexibility .Automotive paint, baking paint for industrial
348	Ethers/Aromatics	58~62	≤3	Transparency	20~30/CPS	70	≤8	Good leveling and weather resistant. Coil top coat
328-1	Ethers/Aromatics	43~47	≤3	Transparency	20~25/CPS	5	≤8	Good adhesion. Coil base coat
305	Ethers/Aromatics	58~62	≤3	Transparency	50~70/CPS	35	≤8	Combination properties. General coil base coat, top coat and back coat
306	Ethers/Aromatics	58~62	≤3	Transparency	25~45/CPS	45~55	≤8	Economic high quality amino baking paint, coil top coat
3268	Ethers/Aromatics	48~52	≤3	Transparency	20~30/CPS	35	≤8	Good adhesion, coil base coat, back coat
350	Ethers/Aromatics	58~62	≤3	Transparency	25~35/CPS	65	≤8	Good adhesion, coil base coat, back coat
370	Ethers/Aromatics	58~62	≤3	Transparency	15~25/CPS	120	≤6	High gloss, hardness, coil top coat, coil aluminum coat
376	Ethers/Aromatics	58~62	≤3	Transparency	250~350/T-4	70~80	≤5	Combination prosperities, more economic coil coat compared with 335
362	Ethers/Aromatics	58~62	≤3	Transparency	15~25/CPS	25	≤6	Good adhesion, coil back coat
352	Ethers/Aromatics	58~62	≤3	Transparency	15~25/CPS	25	≤6	Good hardness, toughness and balance, coil base coat
327	Ethers/Aromatics	58~62	≤3	Transparency	60~100/CPS	120	≤8	Good hardness, coil back coat
360	Ethers/Aromatics	58~62	≤3	Transparency	20~30/CPS	/	≤8	Good hardness and flexibility, coil top coat
323A	Ethers/Aromatics	53~57	≤3	Transparency	1200~2200EDDY		≤12	Good brushing property, amino baking paint, can coating